

## AFC3000

### Aluminium Laminated Fibreglass Carrier Bituminous Membrane 3 mm

#### Product Description

Plastomeric waterproofing cover with APP  
(Atactic polypropylene) additive

60 g/m<sup>2</sup> with Fiberglass carrier

One side is polyethylene film, the other side  
is aluminum laminated.

#### Areas of Use

It is used as second layer in chimney  
insulations, second layer in dome and  
Vaulted roofs, and second floor in secret  
creek insulations.

#### Application Form

It is applied full, dotted or free with 10 cm at  
the joints and 15 cm at the end of the roll  
with the torch flame.

#### Thickness

3 mm

#### Roll Length

10 mt.



#### Storage & Protection

The rolls are stocked vertically in a closed  
environment.

They should not be exposed to ultraviolet  
rays and sudden changes in temperature.

If the rolls need to be stored in the open  
area for a long time, they must be covered to  
protect them from the sun's rays.

After application, piercing and cutting should  
not be done.

Rolls are not placed on top of each other if  
they are to be stacked without pallets.

In palletized stacking, it can be placed on top  
of each other with two rows of chipboard at  
the bottom.

The terraces that are visited should be  
protected by floor covering

Technical Specifications	Test Name	Standart	Unit	Measurement Results
	Tensile Strength (Width - Length)	TS EN 12311-1	N/5 cm	200-300
	Breaking Elongation (Width - Length)	TS EN 12344-1	%	2-2
	Waterproof	TS prEN 1928		Waterproof
	Flow Resistance	TS 11758-1	°C	110
	Dimensional Stability	TS EN 1107-1	%	0.5
	Cold Shrinkage	TS EN 1109	°C	-5
	Tear Strength	TS EN 12310-1	N/5 cm	75
Dimensions	Thickness	TS EN 1849-1	mm	2
	Roll Length	TS EN 11758-1	m	10
	Roll Width	TS 11758-1	m	1
	Roll Weight		Kg.(min.)	33
	Bottom-Top Surface			PE/PE