

FC3000 Fibreglass Carrier Bituminous Membrane 3 mm

Product Description

Plastomeric waterproofing cover with APP (Atactic polypropylene) additive

60 gr / m² with Fiberglass carrier

Both sides are covered with polyethylene film

Areas of Use

Water and steam insulation of wet places,

Single or double floor insulation for retaining and basement walls,

As a single or double layer in pressurized groundwater problems,

As the first layer in secret creek insulation.

Application Form

It is applied full, dotted or free with 10 cm at the joints and 15 cm at the end of the roll with the torch flame.

Roll Length

10 mt.



Storage & Protection

The rolls are stocked vertically in a closed environment.

They should not be exposed to ultraviolet rays and sudden changes in temperature. Period of time, they should be covered to protect them from the sun's rays.

After application, piercing and cutting should not be done.

Rolls are not placed on top of each other if they are to be stacked without pallets.

In palletized stacking, it can be placed on top of each other with two rows of chipboard at the bottom.

The terraces that are visited should be protected by floor covering

Technical Specifications	Test Name	Standart	Unit	Measurement Results
Tensile Strength	(Width - Length) TS EN	12311-1	N/5 cm	200-300
Breaking Elongation	(Width - Length) TS EN	12344-1	%	2-2
Waterproof	TS prEN	1928		Waterproof
Flow Resistance	TS	11758-1	°C	110
Dimensional Stability	TS EN	1107-1	%	0.5
Cold Shrinkage	TS EN	1109	°C	-5
Tear Strength	TS EN	12310-1	N/5 cm	75
Dimensions Thickness	TS EN	1849-1	mm	2
Roll Length	TS EN	11758-1	m	10
Roll Width	TS	11758-1	m	1
Roll Weight			Kg.(min.)	34
	Bottom-Top Surface			PE/PE